


William N. Lamarre Concrete Products, Inc.

6' DIAMETER LEACHING CATCH BASIN

1000 Gallons
 Available H10 & HD Top Loading
 Drawing Not to Scale



Notes

1. Concrete strength f'c 4000PSI@28 days. Density 150 PCF.
2. Cement, Portland Type II or III, ASTM C150-81
3. Admixtures, air & plasticizers per ASTM C233-82